



8100 Series Static Shielding Bags

SPECIFICATIONS

Electrical Properties

	Typical Values	Test Method
Surface Resistance:		
Outer Surface	<10E11 ohms	EOS/ESD S11.11
Aluminum Layer	<10E2 ohms	EOS/ESD S11.11
Inner Surface	<10E11 ohms	EOS/ESD S11.11
Static Shielding	<25nJ	EOS/ESD S11.31
Charge Generation	Teflon: 0.09 nC/sq.in. Quartz: 0.01 nC/sq.in.	Modified Incline Plane Modified Incline Plane
Capacitance Probe (to dissipate 1 KV)	<30V	MIL-PRF-81705D, EIA 541

Physical Properties

Bag Thickness:		
Polyester Layer	0.5 Mils Static Dissipative PET Film	ASTM D-2103
Aluminum Layer	10-25 Angstroms	
Polyethylene Layer	2.5 Mils Static Dissipative PE film	ASTM D-2103
Total Thickness	3.0 Mils	ASTM D-2103
Light Transmission (%)	>40% (Tobias)	ASTM D-1003
Burst Strength (psi)	>50	FTMS 101K, Method 2065.1
Heat Seal (lbs/in)	>10	375° F, ½ sec 60 psi
Seam Strength	Pass	MIL-PRF-81705D
Tear Strength (lbs)	>25	ASTM D-1004
Puncture Resistance (lbs)	>10	ASTM D-2065
MVTR (gms / 100 in ² / 24 hrs, 100°F)	<0.40	FTMS 101C/2065
OTR (cc / 100 in ² / 24 hrs)	<6.1	ASTM D-1434
Abrasion Resistance	>100 cycles	Sutherland Abr. (.0000 Steel Wool)
Outgassing	Pass	ASTM E595
Non-corrosive	Pass	MIL-STD-3010, M3005

Chemical Properties

Corrosion	No effect on aluminum, copper, silver, SN-Pb coated foil, stainless Steel, low carbon steel	
Polycarbonate Capability	Yes	
No Amines or N-Octanoic Acid	Not present	

Bag is free of amines, N-Octanoic acid, and heavy metals.
These bags are recyclable.

CORPORATE OFFICES: 888 Dayton St., Suite 105, Yellow Springs, OH 45387 www.4bennett.com
CUSTOMER SERVICE NUMBERS: (888) 4 BENNETT Phone: (937) 324-1100 Fax: (937) 324-8753



**For more information regarding this product, please contact us toll-free at
(888) 4-BENNETT**

This document is prepared for our customers as a service, and is, to the best of our knowledge, true and accurate. However, it is understood and agreed by the users of this document that we will accept no liability for the conclusions reached. In addition, the products discussed are sold without warranty, expressed or implied, and this document is not to be construed as making any such warranties. Users of this document may therefore wish to perform additional testing before determining that products mentioned are suitable.

Copyright 2006 – Bennett & Bennett, Inc. – All Rights Reserved

**CORPORATE OFFICES: 888 Dayton St., Suite 105, Yellow Springs, OH 45387 www.4bennett.com
CUSTOMER SERVICE NUMBERS: (888) 4 BENNETT Phone: (937) 324-1100 Fax: (937) 324-8753**